Technical Data Sheet

Ace Timberlac Series

Description

Diamond Ace Timberlac Sanding Sealer is a semi-gloss, transparent, high-build sealer. It is designed to seal small fine wood pores. Sanding sealer is suitable for all types of interior wood, furniture, doors, windows and wooden floors etc.

Recommended use

Diamond Ace Timberlac Sanding Sealer is recommended to use on wood and wooden products to fill the pores in order to get the better finish.

Physical properties

Colour Pale Yellow, Dried film transparent

Finish Satin
Solids (vol %)* 36 ± 2 Flash point $23 \, ^{\circ}C$ Specific Gravity 0.95 - 1.00

Film Thickness and Spreading Rate

Film Thickness 30 microns dft
Spreading rate 12-14 (m²/ Ltr/Coat)

Surface Preparation

Ensure surface is dry and free from oil, grease, dust etc.

Application

Application Method



Spray (airless or conventional) Muslin Cloth Pad

Cleaning Ace Timberlac Premium Thinner

Thinning 40 - 50 % Ace Timberlac Premium Thinner

Drying Time

Temperature	Dry to Touch	Dry to Handle	Recoating Time
25 °C	20 minutes	4 hours	1 hour
35 °C	15 minutes	3 hours	40 minutes

Typical paint system

On wood

Diamond Ace Timberlac Sanding Sealer Several coats to attain

smooth finish

Diamond Ace Timberlac Gloss Lacquer 2 Coats

Or

Diamond Ace Timberlac Matt Lacquer 2 Coats

Ace Timberlac Sanding Sealer



Storage

The product must be stored in accordance to the national regulations. The product should be kept in a well-ventilated place, protected from heat and direct sunlight. The containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing Size

0.91 Ltr, 3.64 Ltrs, 20 Ltrs.

Health and Safety

Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapours and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.

