# **Technical Data Sheet**

**Ace Series** 

#### **Description**

Diamond Ace Hi Sparkle Metallic is a top quality paint which gives a sparkling and lustrous finish as well as extreme protection against water, rust and dust.

#### **Recommended Use**

Formulated for use on pre-primed steel surface as finishing coat where glossy decorative high sparkling metallic finish is required.

# **Physical Properties**

Colour Standard Colour Range

Finish Gloss
Solids (vol %)\*  $46 \pm 2$ Flash Point  $23 \,^{\circ}\text{C}$ Specific Gravity 0.90 - 1.05

# **Film Thickness and Spreading Rate**

Film Thickness 30 microns dft
Spreading Rate 13-15 (m²/ Ltr/Coat)

# **Surface Preparation**

Pre-primed or on smooth surfaces. Ensure that surface is clean, dry and free from rust, grease, oil and other contamination.

# **Application**

Application Methods Spray (airless or conventional)

Mixing Ratio (volume) Single Pack

Cleaning Mineral Turpentine

Thinning 10-20 % Mineral Turpentine

#### **Drying Time**

Temperature	Dry to Touch	Dry to Handle	Recoating Time
25 °C	6 hours	12 hours	12 hours
35 °C	3 hours	8 hours	12 hours

# **Typical Paint System**

On Steel

Diamond Overall Undercoat / Red Oxide Primer 1 Coat
Diamond Ace Hi-Sparkle Metallic 2 Coats

# Ace Hi Sparkle Metallic



# **Storage**

The product must be stored in accordance to the national regulations. The product should be kept in a well-ventilated place, protected from the heat and direct sunlight. The containers must be kept tightly closed.

#### Handling

Handle with care. Stirr well before use.t.

#### **Packing Size**

0.91 Ltr and 3.64 Ltrs.

# **Health and Safety**

Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist/vapours and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.

