

Technical Data Sheet

Ace Series

Description

Diamond Ace Super Gloss Enamel is a supreme quality oil-based enamel which results in a hard, durable, glossy finish and has maximum gloss retention.

Recommended Use

Recommended for exterior / interior use on wood, metal, plaster, concrete, gypsum, brickwork and asbestos surfaces where long lasting and high gloss washable finish is required.

Physical Properties

Colour	Standard Colour Range
Finish	Gloss
Solids (vol %)*	43 ± 2
Flash Point	> 34 °C
Specific Gravity	0.90 – 1.15




Film Thickness and Spreading Rate

Film Thickness	30 microns dft
Spreading Rate	13 - 15 (m ² / Ltr/ Coat)

Surface Preparation

Pre-primed or on smooth surface, ensure that surface is clean, dry and free from rust, dust, grease, oil and other contamination.

Application

Application Methods  Brush  Roller  Spray

Cleaning Mineral Turpentine

Thinning 10 - 20 % Mineral Turpentine

Drying Time

Temperature	Dry to Touch	Dry to Handle	Recoating Time
25 °C	4 hours	16 hours	16 hours
35 °C	3 hours	12 hours	12 hours

Typical Paint System

On Steel

Diamond Red Oxide Primer/Undercoat	1 Coat
Diamond Ace Super Gloss Enamel	2-3 Coats

Ace Super Gloss Enamel



Storage

The product must be stored in accordance to the national regulations. The product should be kept in a well-ventilated place, protected from the heat and direct sunlight. The containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing Size

0.91 Ltr, 3.64 Ltrs and 14.56 Ltrs.

Health and Safety

Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist/vapours and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.



Pakistan's No.1 Paint