# **Technical Data Sheet**

### **Description**

Diamond Value Plus Emulsion is a high PVC decorative paint.

#### **Recommended Use**

Recommended for use on plaster, concrete, gypsum, brick work and asbestos surfaces. (For interior surfaces only).

### **Physical Properties**

Colour Standard Colour Range

Finish Matt Solids (vol %)\*  $47 \pm 2$ 

None - Water Based Flash Point

Specific Gravity 1.40 - 1.50

### Film Thickness and Spreading Rate

Film Thickness 30 microns dft 12-14 (m<sup>2</sup> / Ltr / Coat) Spreading Rate

### **Surface Preparation**

All loose material including loose plaster, cement splashes, old paint, dust, etc. must be thoroughly removed. New plaster / concrete must be fully cured.

### **Application Data**

**Application Method** Spray (airless or conventional), Brush, Roller.

Thinner / Cleaner Clean Water

Thinning 50-70% with Clean water

### **Application**

**Application Methods** 







Cleaning Clean Water

**Thinning** 50 - 70 % with Clean Water

### **Drying Time**

Temperature	Dry to Touch	Dry to Handle	Recoating Time
25 °C	30 minutes	2 hours	3 hours
35 °C	15 minutes	1 hour	2 hours

### **Typical Paint System**

### On Plaster / Concrete

Diamond Overall Water Based Acrylic Primer 1 Coat Diamond Value Plus Wall Putty 2 Coats Diamond Value Plus Emulsion 2-3 Coats

## Value Plus Emulsion



### Storage

The product must be stored in accordance to the national regulations. The product should be kept in a well-ventilated place, protected from the heat and direct sunlight. The containers must be kept tightly closed.

### Handling

Handle with care. Stirr well before use.t.

### **Packing Size**

3.64 Ltrs and 14.56 Ltrs.

### **Health and Safety**

Material health and safety data sheet is available upon request. Please observe the precautionary notice displayed on the container. Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist/vapours and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.

